



VICLAB GENERAL

TEST REPORT

Sample As Received	Reference: General	Last Revised: 5/05/2015
Report No: 150314		Order #:
Date Received: 10/03/2015		Date Completed: 5/05/2015
Client: AUSTEX COMMERCIAL FABRICS		Telephone: +61 3 9484 9744
Address: 15-19 Heyington Avenue, Thomastown VIC 3074		Submitted By: Danny Mignone

Sample Description: Studio Encore, 85% P.V.C. and 15% Polyester White swatch as supplied

Test Description	Method
Wear	AS 1441.12:1993 Abrading Machine

Temperature at time of test: 21°C.

Clause 2.16 Wear

Table No. 1

Grade	Minimum Cycles	Comment
KE1 Heavy Duty	50,000	No discoloration or excessive loss of grain.

Comments: The material passes the wear test. Upon request abrasion taken to 1,000,120 cycles. The results were as follows:

Cycles	Performance
1,000	Very slight polishing of surface.
10,000	Slight polishing of surface.
50,000	Slight polishing of surface, very slight compression of surface pattern.
100,000	* Slight polishing of surface, very slight compression of surface pattern.
150,000	Slight polishing of surface, very slight compression of surface pattern.
200,000	* Slight polishing of surface, very slight compression of surface pattern.
300,000	* Slight polishing of surface, moderate compression of surface pattern.
400,000	* Slight polishing of surface, moderate compression of surface pattern.
500,000	* Moderate polishing of surface, moderate compression of surface pattern.
600,000	* Moderate polishing of surface, moderate compression of surface pattern.
700,000	* Moderate polishing of surface, moderate compression of surface pattern.
800,000	* Moderate polishing of surface, moderate compression of surface pattern.
900,000	* Severe polishing of surface, severe compression of surface pattern.
1,000,000	* Severe polishing of surface, very severe compression of surface pattern.
1,000,120	Severe polishing of surface, very severe compression of surface pattern. Test ended.

* indicates new abrading surface applied.



NATA Accredited Laboratory
Number: 14722

This document is issued in accordance with NATA accreditation requirements.
Accredited for compliance with ISO/IEC 17025
The results of the tests, calibrations and/or measurements in this document are traceable to Australian National Standards.
This document shall not be reproduced except in full

AUTHORISED SIGNATORY:

Legend:
NA = Not Applicable
NT = Not Tested
NS = Not Supplied
TBA = To Be Ascertained

